

### 1. Product Description

Product description	: SOMAFIX MULTI PURPOSE NEUTRAL SILICONE is neutral, one component % 100 silicone. It is used in building construction, inner and outer profiles with vast scope of applications.
Product form	: Mixture
Trade name	: SOMAFIX MULTI PURPOSE NEUTRAL SILICONE
Use of the substance/mixture	: Adhesives, sealants
Recommended use	: Consumer use Industrial use Professional uses
Type of product	: Adhesives, sealants

### 2. Characteristics

Characteristics	: Solvent-free Non-yellowing Flexible No shrinkage Colourfast Unpaintable Mold retardant Non-sag Non-tacky surface Easy gunnability High end DIY quality Low shrinkage Low odour Excellent appearance Good tooling properties Non-corrosive to metals
-----------------	--

### 3. Application

- Exhibiting good primerless adhesion to most material used for sanitary application, e.g. glass, tiles, ceramics, enamel, glazed tiles and clinker; metals e.g. aluminium, steel, zinc or copper; impregnated, varnished or painted wood, concrete, brick and many plastics
- Using as a filler and sealer on door and window installation, on building facades, in kitchen and bathrooms
- Suitable for alkaline substrates such as concrete, mortar, fibrous cement

### 4. Application Instructions

- Application temperature is between +5 °C to +40 °C.
- Make sure the surface to be applied is dry and clean, free of dust and grease
- Cut the cartridge/sausage tip and place it in the gun
- Clean any silicone residue simply with soapy water
- Joint width and depth ratio should be about 2:1

### 5. Technical Specifications (@ 23 °C 50% RH)

Physical state	: Solid
Chemical Basis	: Neutral.
Appearance	: Paste.
Odour	: characteristic

Curing System	: Moisture
Skin Forming Time	: 5 – 20 minutes
Curing Rate	: 4 – 5 mm/day
Elongation at Break	: 200 %
Tensile Strength	: 0.6 N/mm <sup>2</sup>
Hardness Shore A	: 24
Density	: 1.01 g/cm <sup>3</sup> ±0,01 @23°C
Viscosity, kinematic	: Not applicable
Flash point	: Not applicable
Thermal Resistance	: -40 – 180 °C
Application Temperature	: 5 → 40 °C

## 6. Packaging

<b>Packaging</b>	: Original packaging
<b>Colour</b>	: Transparent. white. Black.

Cartridge 280 ml	Package 24 pcs/ctn
Cartridge 310 ml	Package 24 pcs/ctn
Sausage 600 ml	Package 20 pcs/ctn

## 7. Shelf Life and Storage

Storage conditions	: Store in a well-ventilated place. Keep cool.
Storage temperature	: 0 → 35 °C

Cartridge 280 ml	18 months (after production date if stored at room temperature)
Cartridge 310 ml	18 months (after production date if stored at room temperature)
Sausage 600 ml	18 months (after production date if stored at room temperature)

## 8. Health and Safety

Adverse physicochemical, human health and environmental effects	: To our knowledge, this product does not present any particular risk, provided it is handled in accordance with good occupational hygiene and safety practice
First-aid measures after inhalation	: Remove person to fresh air and keep comfortable for breathing.
First-aid measures after skin contact	: Wash skin with plenty of water.
First-aid measures after eye contact	: Rinse eyes with water as a precaution.
First-aid measures after ingestion	: Call a poison center or a doctor if you feel unwell.
Other medical advice or treatment	: Treat symptomatically.
Hand protection	: Protective gloves
Eye protection	: Safety glasses
Skin and body protection	: Wear suitable protective clothing
Respiratory protection	: In case of insufficient ventilation, wear suitable respiratory equipment

## 9. Remarks

Remarks	: For further information, please refer to the Safety Data Sheet
---------	--

## 10. Standards and Certificates

Standards and Certificates	: EN 15651-1 EN 15651-2
----------------------------	----------------------------



# SOMAFIX MULTI PURPOSE NEUTRAL SILICONE

## Technical Data Sheet

Issue date: 09/03/2017

Revision date: 01/04/2024

Version: 0.4

TDS No.: TDS.09.30

### Technical Data Sheet

*DISCLAIMER OF LIABILITY* The information in this SDS was obtained from sources which we believe are reliable. However, the information is provided without any warranty, express or implied, regarding its correctness. The conditions or methods of handling, storage, use or disposal of the product are beyond our control and may be beyond our knowledge. For this and other reasons, we do not assume responsibility and expressly disclaim liability for loss, damage or expense arising out of or in any way connected with the handling, storage, use or disposal of the product. This SDS was prepared and is to be used only for this product. If the product is used as a component in another product, this SDS information may not be applicable